

PRV

PATENT- OCH REGISTRERINGSVERKET
Patentavdelningen


PCT/SE 2004 / 001724

REC'D 08 DEC 2004	
WIPO	PCT

Intyg Certificate

Härmed intygas att bifogade kopior överensstämmer med de handlingar som ursprungligen ingivits till Patent- och registreringsverket i nedannämnda ansökan.

This is to certify that the annexed is a true copy of the documents as originally filed with the Patent- and Registration Office in connection with the following patent application.



(71) Sökande Pergo (Europe) AB, Trelleborg SE
Applicant (s)

(21) Patentansökningsnummer 0303147-3
Patent application number

(86) Ingivningsdatum 2003-11-25
Date of filing

Stockholm, 2004-11-30

För Patent- och registreringsverket
For the Patent- and Registration Office


Görel Gustafsson

Avgift
Fee

**PRIORITY
DOCUMENT**
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

BEST AVAILABLE COPY

**PATENT- OCH
REGISTRERINGSVERKET
SWEDEN**

Postadress/Adress
Box 5055
S-102 42 STOCKHOLM

Telefon/Phone
+46 8 782 25 00
Vx 08-782 25 00

Telex
17978
PATOREG S

Telefax
+46 8 666 02 86
08-666 02 86

A process for the manufacture of decorative surface elements with a surface structure.

The present invention relates to a process for the manufacture of decorative surface elements with a surface structure.

Products coated with simulated versions of materials such as wood and marble are frequent today. They are foremost used where a less expensive material is desired, but also where resistance towards abrasion, indentation and different chemicals and moisture is required. As an example of such products floors, floor beadings, table tops, work tops and wall panels can be mentioned.

As an example of an existing product can be mentioned the thermosetting laminate which mostly consists of a base with a decor sheet placed closest to the surface. The decor sheet can be provided with a desired decor or pattern. It is also common to arrange a wear layer on top of the decor sheet in order to protect it from wear. The decorative surface is most often provided with a surface structure during the lamination in order to increase the decorative effect. This is achieved by utilising a press belt, a press foil or a press plate, provided with structured surface, which is pressed towards the surface during the lamination procedure.

According to the present invention it has been made possible to manufacture decorative surface elements where the

The process can be used when manufacturing surface elements like floor boards, wall panels and ceiling panels. Accordingly, the invention relates to a process for the manufacturing of a decorative surface element. The element comprises a core material, a decorative surface layer and a protective upper wear layer. At least one of said decorative surface layer and said wear layer comprises a thermosetting resin. The invention is characterised in that the process comprises the steps;

- a) The upper surface of the core material is provided with a surface structure.
- b) The decorative surface layer is then applied on top of the surface structured

core.

c) The protective wear layer is then applied on the decorative surface layer.

d) The core material, the decorative layer and the wear layer is then pressed under increased pressure and temperature in a laminate press so that resin cures and the different layers are bonded to one to the other.

According to one embodiment of the invention the surface structure of the core material is achieved by milling a desired surface into the upper surface of the core material.

According to another embodiment of the invention the surface structure of the core material is achieved by pressing a structured press plate or press roller on top of the upper surface of the core material.

According to yet another embodiment of the invention the surface structure of the core material is achieved by rolling the core material between at least one surface structured calendar roller and a counter-stay roller.

According to yet another embodiment of the invention the surface structure of the core material is achieved by partially wetting the upper surface of the core material with a solvent.

According to yet another embodiment of the invention the surface structure of the core is achieved by wetting the upper surface of the core material with a solvent whereupon a structured press plate or roller is pressed onto said upper surface.

The decorative surface layer suitably comprises a cellulose sheet impregnated with an amino resin. The amino resin is suitably selected from the group consisting of melamine formaldehyde resin, urea formaldehyde resin and mixtures thereof.

The wear layer suitably also comprises a cellulose sheet impregnated with an amino resin selected from the group consisting of melamine formaldehyde resin, urea formaldehyde resin and mixtures thereof. It is of course possible to use more than one such cellulose sheets in the wear layer for increased wear resistance.

The wear layer may further comprise hard particles selected from the group consisting of aluminium oxide, silicon oxide and silicon carbide having an average

particle size in the range 50 nm - 150 μ m in order to further increase the wear resistance. The scratch resistance may be increased by providing the uppermost surface of the wear layer is provided with hard particles selected from the group consisting of aluminium oxide, silicon oxide and silicon carbide having an average particle size in the range 50 nm - 30 μ m.

It is advantageous to utilise a press cushion arranged on top of the wear layer during the pressing.

It is alternatively possible to use a press plate having a surface structure matching the surface structure of the core material is arranged on top of the wear layer during the pressing. This does however require that the structure on the surface of the base material is accurately machined to match the structure of the press plate.

The surface structure will of course comprise different features and can be described as macro structure and micro structure. The macro structure is in the present invention comprised of the structure arranged on the core material. It will here be possible to simulate for example the recessed grout line between ceramic tiles as well as the rough irregular surface of the ceramic tile itself. It is also possible to simulate worn wood like when the softer parts of the wood becomes recessed while the resin rich parts of the wood withstand wear and therefore protrudes. The micro structure is used for simulating pores in wood, granular structure, sanding mark structure, milling mark structure, micro cracks and flat to gloss surfaces. It is accordingly suitable to utilise a press foil provided with a micro structure which is arranged on top of the wear layer during the pressing. A press cushion is suitably arranged between the press foil and the press during the pressing.

The base layer suitably consists of a particle board or a fibre board.

CLAIMS

1. A process for the manufacturing of a decorative surface element with surface structure, which element comprises a core material, a decorative surface layer and a protective upper wear layer, where at least one of said decorative surface layer and said wear layer comprises a thermosetting resin, wherein the process comprises the steps;
 - a) providing the upper surface of the core material with a surface structure,
 - b) applying the decorative surface layer on top of the surface structured core,
 - c) applying the protective wear layer on the decorative surface layer,
 - d) pressing the core material, decorative layer and wear layer under increased pressure and temperature in a laminate press so that resin cures and the different layers are bonded to one to the other.
2. A process according to claim 1 wherein the surface structure of the core material is achieved by machining a desired surface into the upper surface of the core material.
3. A process according to claim 1 wherein the surface structure of the core material is achieved by pressing a structured press plate or press roller on top of the upper surface of the core material.
4. A process according to claim 1 wherein the surface structure of the core material is achieved by partially wetting the upper surface of the core material with a solvent.
5. A process according to claim 1 wherein the surface structure of the core is achieved by wetting the upper surface of the core material with a solvent whereupon a structured press plate or roller is pressed onto said upper surface.
6. A process according to claim 1 wherein the surface structure of the core material is achieved by rolling the core material between at least one surface structured calendar roller and a counter-stay roller.

7. A process according to claim 1 wherein the decorative surface layer comprises a cellulose sheet impregnated with an amino resin selected from the group consisting of melamine formaldehyde resin, urea formaldehyde resin and mixtures thereof.
8. A process according to claim 1 wherein the wear layer comprises a cellulose sheet impregnated with an amino resin selected from the group consisting of melamine formaldehyde resin, urea formaldehyde resin and mixtures thereof.
9. A process according to claim 8 wherein the wear layer further comprises hard particles selected from the group consisting of aluminium oxide, silicon oxide and silicon carbide having an average particle size in the range 50 nm - 150 μ m.
10. A process according to claim 8 or 9 wherein the uppermost surface of the wear layer is provided with hard particles selected from the group consisting of aluminium oxide, silicon oxide and silicon carbide having an average particle size in the range 50 nm - 30 μ m.
11. A process according to claim 1 wherein a press cushion is arranged on top of the wear layer during the pressing.
12. A process according to claim 1 wherein a press plate having a surface structure matching the surface structure of the core material is arranged on top of the wear layer during the pressing.
13. A process according to claim 1 wherein a press foil provided with a micro structure is arranged on top of the wear layer during the pressing.
14. A process according to claim 1 wherein a press cushion is arranged between the press foil and the press during the pressing.
15. A process according to claim 1 wherein the base layer consists of a particle board or a fibre board.

ABSTRACTS:

A process for the manufacturing of a decorative surface element with surface structure, which element comprises a core material, a decorative surface layer and a protective upper wear layer. At least one of said decorative surface layer and said wear layer comprises a thermosetting resin. The process comprises the steps of providing the upper surface of the core material with a surface structure, applying the decorative surface layer on top of the surface structured core, applying the protective wear layer on the decorative surface layer and pressing the core material, decorative layer and wear layer under increased pressure and temperature in a laminate press so that resin cures and the different layers are bonded to one to the other.

P
R
V
0
3
-
1
1
-
2
5
N